

Product Description

MetecnoPanel[®] is a durable, insulated wall and ceiling panel with a PIR (Polyisocyanurate) fire-retardant core and high performing thermal properties. MetecnoPanel[®] is FM Approved to FM 4880 & 4881 - No Height Restriction and is recommended where improved fire performance is required for insurance purposes. MetecnoPanel[®] is available in a variety of panel surface profiles and Colorbond[®] colours to create an inspiring interior and exterior finish.

Panel Properties						
Panel Thickness (mm)	50	75	100	125	150	200
Typical Mass (kg/m ²) based on 0.6/0.6mm skins	12.0	13.0	14.0	14.7	15.5	17.4
Declared λ (W/m.K) at 23°C	0.022	0.022	0.022	0.022	0.022	0.022
Declared R-value (m ² K/W) at 15°C (NZ)	2.30	3.50	4.65	5.80	7.00	9.30
Declared R-value (m ² K/W) at 23°C (AU)	2.20	3.35	4.45	5.55	6.70	8.90
Total R-value (m ² K/W) at 6°C	2.61	3.84	5.06	6.29	7.51	9.96
Total R-value (m ² K/W) at 15°C (Winter)	2.49	3.66	4.83	5.99	7.16	9.49
Total R-value (m ² K/W) at 30°C (Summer)	2.31	3.38	4.46	5.53	6.60	8.75

Note: The Declared R-value is at 23°C in accordance with AS/NZS 4859.1:2018 & AS/NZS 4859.2:2018.

Span Table

NON-CYCLONIC REGION A&B (WALL APPLICATIONS ONLY)

PIR Core / 0.6mm Steel Skins (contact Metecno for other skin materials)
 Maximum uniformly distributed ultimate wind load (kPa) for the given span:

Single Span, wind pressure acting inwards/outwards						
Span (mm)	Panel Thickness (mm)					
	50	75	100	125	150	200
1500	2.93	4.39	5.86	7.32	8.79	11.72
2700	1.63	2.44	3.25	4.07	4.88	6.51
3900	1.10	1.65	2.20	2.74	3.29	4.39
5100	0.64	0.96	1.28	1.60	1.93	2.57
6300	0.37	0.63	0.84	1.05	1.26	1.68
7500	0.23	0.45	0.59	0.74	0.89	1.19

Multi-Span, wind pressure acting inwards/outwards						
Span (mm)	Panel Thickness (mm)					
	50	75	100	125	150	200
1500	3.91	5.86	7.81	9.33	11.72	11.93
2700	2.17	3.25	4.34	5.18	6.51	6.63
3900	1.10	1.65	2.20	2.74	3.29	4.39
5100	0.64	0.96	1.28	1.60	1.93	2.57
6300	0.42	0.63	0.84	1.05	1.26	1.68
7500	0.30	0.45	0.59	0.74	0.89	1.19



Colorbond[®]

 **BAL40**



 **FM APPROVED**

CODEMARK
Australia
Certificate CM40196

Core	PIR (Fire-retardant Polyisocyanurate)
Width (cover mm)	1100, 1200 (available upon request)
Thickness (mm)	50, 75, 100, 125, 150, 200
Length	Up to 11.8m (For NZ)
External Material	BlueScope [®] Steel 0.5mm, 0.6mm G300, Grade 316 Stainless Steel 0.55mm
External Finishes	Plain, Fineline, Satinline, Ribbed
Exterior Colour Options	Surfmist [®] . Other colours available subject to minimum order quantities.
Internal Material	BlueScope [®] Steel 0.5mm, 0.6mm G300, Grade 316 Stainless Steel 0.55mm
Internal Finishes	Plain, Fineline, Satinline, Ribbed
Interior Colour Options	Coolroom White
Paint System	AS/NZS 2728 & AS 1397
Acoustic Properties	Rw 25 - 27 depending on thickness
Material Group Numbers	C1.10 Group 2 ^a
Bushfire Attack Level	BAL-40 200mm - BAL-FZ (All exposed core to be covered with flashing)
FM Approval	4880, 4881
Environmental	Zero Ozone Depleting Potential (ODP)
Fire Hazard Properties	AS/NZS 1530.3
Ignitability Index	0
Spread of Flame Index	0
Heat Evolved Index	0
Smoke Index	4
SMOGR _{RC}	< 100

a. AS 5637.1 / AS ISO 9705 - BCA Group Number (Spec C1.10)
 MetecnoPanel[®] PIR steel skinned insulated building panels conform to the requirements of the BCA Specification C1.10 Group 2.


Group 2
 Panel up to 200mm thick with aluminium 'wall-wall' and 'wall-ceiling' angles (1.5mm) fixed with aluminium rivets or screws is classified as Group 2. Panel up to 200mm with steel 'wall-wall' and 'wall-ceiling' angles (0.5mm) fixed with steel rivets or screws is classified as Group 2.

The technical information contained in this document cover a breadth of applications where MetecnoPanel[®] may be used, which may be outside the scope of our Codemark certificate. Data specific to CodeMark certification can be found on MetecnoPanel[®]'s CoC CM40196.


SPAN TABLE NOTES:

- Extended span tables including cyclonic regions C&D are also available. Refer Metecno[®].
- Fixing with min. 14g tek screws (x4 off) or mushroom head bolts (x2 off) per fixing point are required.
- Pressures specified are for wind gusts only per AS/NZS 1170.2.
- Deflection limit of span/150 applies, and in accordance with Serviceability Limit State criteria per AS/NZS 1170.0 - TABLE C1. Metecno[®] tests comply with details outlined in AS 4040.0, AS 4040.1, AS 4040.2, AS 4040.3, AS 1562.1 and AS/NZS 1170.1.


Joint



Profiles



Dimensions



Contact

MetecnoPIR
111 Ingram Road
Acacia Ridge QLD 4110
T: 07 3323 9900
F: 07 3323 9905
Email: enquiry@metenopir.com.au

Metecno Pty Limited. ABN 44 096 402 934. The manufacturer reserves the right to change the specification without notice. Metecno PIR[®], MetecnoInfinite[®], MetecnoKasset[®], MetecnoPanel[®], MetecnoSpan[®] and EconoClad[®] are trademarks of Metecno Pty Limited. The colours shown in this publication have been reproduced to represent actual product colours as accurately as possible. However, given printing limitations, we recommend checking your chosen colour against an actual sample before placing orders. Panel profiles shown in this publication are indicative only. Refer to engineering for exact specifications. This advice is of a general nature only. Designers must provide for adequate structural performance and other Building Code requirements. This information is subject to change.

*Warranty subject to exclusions, application and eligibility criteria. For full terms and conditions and to determine the eligibility of your project for the warranty visit bluescopesteel.com.au/warranties or call BlueScope on 1800 022 999. Colorbond[®], Permagard[®] and BlueScope are registered trademarks of BlueScope Steel Limited.

Refer to Metecno PIR[®] website for latest version. Consult Metecno PIR[®] for your application.